

U.S. National Stage of
PCT/JP00/05692
PRELIMINARY AMENDMENT

comprising another film (C layer) laminated as the opposite outermost layer to form a laminated structure comprising at least three layers including the A layer, the B layer and the C layer.

a2
cont

16. (Amended) A biaxially oriented film according to Claim 15, wherein a surface roughness Ra_A on the A layer side is 0.2 to 10 nm, a surface roughness Ra_C on the C layer side is 1 to 30 nm, and Ra_C is larger than Ra_A .

a3

27. (Amended) A magnetic recording medium comprising a biaxially oriented film according to Claim 1, and a magnetic layer provided on one side of the biaxially oriented film.

Please add new claims 30-32:

a4

30. (New) A biaxially oriented film according to Claim 2, wherein the height of the micro protrusions is 2 to 30 nm.